

**Client's name** : HOANG HA INDUSTRIAL GROUP JOINT STOCK COMPANY  
*Tên khách hàng* : CÔNG TY CỔ PHẦN TẬP ĐOÀN CÔNG NGHIỆP HOÀNG HÀ

**Client's address** : 26A LANE 898 LANG ROAD , LANG THUONG WARD, DONG DA DISTRICT, HA NOI CITY, VIETNAM  
*Địa chỉ* : SỐ 26A, NGÕ 898, ĐƯỜNG LÁNG, PHƯỜNG LÁNG THƯỢNG, QUẬN ĐÔNG ĐA, THÀNH PHỐ HÀ NỘI, VIỆT NAM

**The following sample(s) was/were submitted and identified by the client as:**

*Các thông tin nhận dạng mẫu do khách hàng cung cấp:*

**Name of sample / Tên mẫu** : KEO DÁN SÀN VINYL LOCK A365

**Quantity / Số lượng mẫu** : 01 sample / mẫu


**Description / Mô tả mẫu** : Includings / Bao gồm :  
- 01 box containing adhesive/ 01 thùng chứa keo dán (12kg)  
- 11 vinyl flooring sheets/ 11 tấm sàn vinyl

**Date of receiving / Ngày nhận mẫu** : 12-Dec-2023

**Date of testing / Ngày thử nghiệm** : From / từ 12-Dec-2023 to / đến 11-Jan-2024

**Test result / Kết quả thử nghiệm** : See next page(s) / Xem trang sau

Signed for and on behalf of  
SGS Vietnam LTD



**Luu Van Trung**  
Laboratory Supervisor  
Industrial Services

003922

This document is issued by the Company under its General Conditions of Service accessible at <https://www.sgs.com/en-vn/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Characteristic <i>Tên chỉ tiêu</i>	Unit <i>Đơn vị</i>	Test method <i>Phương pháp thử nghiệm</i>	Test result <i>Kết quả thử nghiệm</i>
1. Shear strength at 7 days <sup>(a)</sup> <i>Độ bền cắt tại 7 ngày</i>	MPa	BS EN 1373 : 2000	0.225
2. Volatile organic compounds (VOC) at 7 days <i>Hàm lượng chất hữu cơ bay hơi tại 7 ngày</i>	%m/m	ISO 11890-2 : 2013	<0.1

**Note / Ghi chú:**

(a) Test conditions / Điều kiện thử nghiệm:

- Lab environmental conditions / Điều kiện môi trường phòng thử nghiệm : (23±2) °C, (50±10) %RH.
- Test speed: 20mm/min / Tốc độ thử: 20 mm/phút.

**Original sample photo(s) / Hình ảnh mẫu nhận:**

 <p><b>Flooring Adhesive / Keo Dán Sàn</b></p>	 <p><b>Vinyl flooring sheets / Tấm sàn vinyl</b></p>
<p>SGS authenticate the photos on original report only / SGS chỉ xác thực các hình ảnh trong báo cáo chính thức</p>	

\*\*\* END OF THE REPORT \*\*\*

003888

This document is issued by the Company under its General Conditions of Service accessible at <https://www.sgs.com/en-vn/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.