

PRODUCT DATA SHEET

LOCK A365

Universal Flooring Adhesive



DESCRIPTION

IBTECO LOCK A365 is a single component, dispersion-based adhesive for laying LVT, PVC and VCT floorings in sheets, tiles, planks and carpet tiles on internal levelled subfloors.

FEATURES & BENEFITS

- ▶ Fast: very fast drying time
- ▶ Efficient: extremely fast installation of large areas
- ▶ Clean: no risk of soiled floor covering
- ▶ Versatile application: useable for trowel and roller application
- ▶ Ease of application with extra long open time
- ▶ Universal: extra long tack for carpet tile installation

SUBSTRATE PREPARATION

Subfloors must be level, permanently dry (concrete moisture <6%), solid and free from cracks, dirt and adhesion-inhibiting substances. Use our self-levelling IBTECO G-812 for areas with rough surfaces

APPLICATION

Stir LOCK A365 well before using. Apply evenly on the subfloor with a suitable trowel or roller, work from out of the container and avoid adhesive pools.

Fit flooring after corresponding airing time of LOCK A365 and press down firmly.

After fitting, roll the complete area again with the roller.



COVERAGE

Depending on the surface structure and absorbability of the subfloor. Approximately 250 - 300g/m² with using A1 trowel, on a flat smooth surface. Coverage may vary if different trowel size is used.

TECHNICAL DATA

Raw material base	Copolymer acrylic
Color	white cream
pH	6-8
viscosity	45,000 to 55,000 cps
c.o.v.	<0.05 g/m ³
percentage of solid	66 %
customs code	3506 9190
application temperature	+ 5°C + 40°C
waiting time	15 - 20 minutes
open time	30 - 40 minutes
setting time	24 hours
Shearing Strength (EN1373)	0.29

PACKAGING

Plastic pail: 12Kg

Code: LOCK A365

STORAGE

LOCK A365 should not be stored in direct contact with sun and protected from freezing. When stored under the correct conditions and unopened, it has a shelf life of 12 months.

SAFETY PRECAUTIONS

Product may produce an allergic reaction. Keep out of reach of children Irritant: Avoid eye and skin contact. Use only in well ventilated areas. Keep container tightly closed. In case of contact with eyes and skin, rinse with plenty of water. In event of irritation, seek for medical advice according to the Material Safety Datasheet available upon request.

THÔNG SỐ KỸ THUẬT

LOCK A365

Keo dán sàn đa năng



MIÊU TẢ

IBTECO LOCK A365 là keo một thành phần gốc Acrylic phân tán để dán sàn LVT, PVC, và sàn VCT dạng tấm dài, dạng gạch vuông, dạng cuộn trên bề mặt nền được làm phẳng.



TÍNH NĂNG & LỢI ÍCH

- ▶ Nhanh: Thời gian khô nhanh
- ▶ Hiệu quả: Lắp đặt rất nhanh trên diện tích lớn
- ▶ Sạch sẽ: Không có nguy cơ làm sàn bị bẩn
- ▶ Ứng dụng linh hoạt: Có thể sử dụng bằng bay hoặc con lăn.
- ▶ Dễ dàng thi công với thời gian mở lâu
- ▶ Phổ thông: Dùng để dán sàn thảm

CHUẨN BỊ BỀ MẶT NỀN

Nền phụ phải phẳng, đã hoàn toàn khô (độ ẩm của nền bê tông phải < 6%), rắn chắc và không có vết nứt, bụi bẩn và chất bám dính.

Sử dụng vữa tự san phẳng IBTECO G-812 của chúng tôi cho những khu vực có bề mặt gỗ ghe

ỨNG DỤNG

Khuấy đều LOCK A365 trước khi sử dụng. Thi công đều trên lớp nền phụ bằng bay hoặc con lăn phù hợp, thi công từ bên ngoài thùng chứa và tránh tạo thành vũng keo.

Lắp sàn sau thời gian mở khô tương ứng của LOCK A365 và ấn mạnh xuống sàn.

Sau khi lắp đặt, cần sử dụng con lăn chuyên dụng lăn toàn bộ bề mặt sàn đã thi công.



ĐỘ BẢO PHỦ

Tùy thuộc vào cấu trúc và khả năng hấp thụ của lớp nền phụ. Khoảng 250g ~ 300g/m² khi sử dụng với bay loại A1 trên bề mặt phẳng nhẵn. Độ phủ có thể thay đổi khi sử dụng bay khác nhau.

THÔNG SỐ KỸ THUẬT

Nguyên liệu gốc cơ sở	Copolymer acrylic
Màu sắc	Trắng kem
Độ pH	6-8
Độ nhớt	45,000 to 55,000 cps
Hàm lượng c.o.v.	<0.05 g/m ³
Tỷ lệ rắn	66 %
Mã hải quan	3506 9190
Nhiệt độ ứng dụng	+ 5°C + 40°C
Thời gian chờ	15 - 20 phút
Thời gian mở	30 - 40 phút
Thời gian đông kết	24 giờ
Độ bền kéo(EN 1373)	0.29

ĐÓNG GÓI

Thùng nhựa: 12Kg

Mã: LOCK A365

BẢO QUẢN

Bảo quản LOCK A365 ở nơi không được tiếp xúc trực tiếp với ánh nắng mặt trời, và tránh bị làm đông. khi được bảo quản trong điều kiện thích hợp và chưa mở nó có thời hạn sử dụng là 12 tháng.

BIỆN PHÁP AN TOÀN

Sản phẩm có thể tạo ra phản ứng dị ứng, để xa tầm tay trẻ em. Kích ứng: Tránh tiếp xúc với mắt và da. Chỉ sử dụng ở những nơi thông gió tốt. Giữ kín thùng chứa, Trong trường hợp tiếp xúc với mắt và da cần phải rửa sạch với nhiều nước. Trong trường hợp bị kích ứng cần liên hệ với cơ sở y tế và tham khảo bảng dữ liệu an toàn vật liệu.